Gardendrain® GR10



GENERAL DESCRIPTION

Gardendrain® GR10 is a composite product made of recycled polypropylene core with a fleece top cover fabric and a non-woven bottom fabric. All three components are bonded together in a single component that is designed for aeration, retention and promoting upward moisture movement.

BASIC USE

Gardendrain® GR10 is specifically designed to act as a drainage, aeration and water retention element in Hydrotech's Extensive Garden Roof® Assembly.



INSTALLATION

- Gardendrain® GR10 is installed as indicated in Hydrotech's Garden Roof® Installation Guidelines.
- Gardendrain® GR10 must be installed white fleece side up.
- Gardendrain® GR10 is a roll product with a 3" wide selvage of extra top fleece along one edge and at the roll end. When installed, the selvage edge is lapped over the top surface of the adjacent GR10 roll.

TECHNICAL DATA

| ILUIIIVICAL DATA | | | |
|--------------------------------|---|--|--|
| ROLL SIZE: | 1.22 metre wide x 15.24 metre long (48 in. x 50 ft) 18.58 square metre (200 sq. ft) | | |
| | coverage per roll | | |
| ROLL WEIGHT: | 1.184 kg/ square metre (0.25 lbs/sq.ft) | | |
| THICKNESS: | Core alone: 10.16 mm (0.40 in.) | | |
| | With fabrics: 10.68 mm approx. (0.42 in. approx.) | | |
| FLOW RATE: | 261 litre/minute/metre (21 gal/min./ft) (ASTM D4716; hydraulic gradient = 1) | | |
| WATER RETENTION | Core alone: 1.711 litre/square metre (0.042 gal/sq. ft) | | |
| | With fabrics 2.03 litre/square metre (0.050 gal/sq. ft) | | |
| COMPRESSIVE STRENGTH: | 719 kNm ² (15,000 psf) (ASTM D1621) | | |
| COVER FABRIC WEIGHT: | 100 grams/square metre (0.0204 lbs/sq. ft) (ASTM D3776) | | |
| COVER FABRIC GRAB TENSILE: | 334/310 N (75/70 lbs) (ASTM D5034) | | |
| COVER FABRIC GRAB ELONGATION: | 40% (ASTM 5034) | | |
| COVER FABRIC GRAB PUNCTURE: | 1,059 N (238 lbs) (ASTM D6241) | | |
| APPARENT OPENING SIZE (AOS) | 0.212 mm (U.S. sieve #70) | | |
| | | | |
| BOTTOM FABRIC WEIGHT: | 129 grams/square metre (0.026 lbs/sq. ft) (ASTM D3776) | | |
| BOTTOM FABRIC GRAB TENSILE: | 445 N (100 lbs) (ASTM D4632) | | |
| BOTTOM FABRIC GRAB ELONGATION: | 50% (ASTM D4632) | | |
| BOTTOM FABRIC CBR PUNCTURE: | 1,113 N (250 lbs) (ASTM D6241) | | |
| | | | |

LEED INFORMATION

| | Credit 4 | Credit 5 | |
|--|-----------------------------|------------------------|---|
| Recycled Content (% by weight) Manufacture Location | 50 (Post-industrial) core | | |
| | <5 (Post-industrial) fabric | | |
| Manufacture Location | | Alpharetta, GA, U.S.A. | |
| Extraction/Harvesting Location | | Alpharetta, GA, U.S.A. | |
| VOC Content (g/L) | | | 0 |

The contents and methods described herein are the intellectual property of Hydrotech Membrane Corp. The information is based on data and knowledge considered to be true and correct at the time of publication and is offered for the user's consideration, investigation and verification. The information is subject to change without notice. The determination of suitability and fitness of the products and the application described herein for a particular purpose are the sole responsibility of the user. Please read all statements, recommendations and suggestions in conjunction with the conditions of sale which apply to all goods sold by Hydrotech Membrane Corp., including the express disclaimers by each company of the implied warranties of merchantability or fitness for a particular purpose.